

## Product Technical Data Sheet

**Mechanically woven Double Twisted Hexagonal shape wire mesh Sack Gabion Box Zinc+Pvc 2.70/3.70mm Mesh Wire, 80X100mm Mesh Opening**

Sr.No	Description	Requirements			Compliance
		Mesh	Selvedge	Lacing	
<b>A</b>	<b>Wire Diameter</b>				
	Zinc Coated Wire Diameter (mm)	2.70	3.40	2.20	IS 16014:2018 table 8
	Tolerance level in diameter (mm)	(+/-)0.07	(+/-)0.09	(+/-)0.06	
<b>B</b>	<b>Tensile Strength &amp; Elongation</b>				
	Tensile Strength Requirement N/mm <sup>2</sup>	350-550 N/mm <sup>2</sup>			IS 16014:2018 clause 6.1
	Elongation Requirement (%)	Minimum 10%			IS 16014:2018 clause 6.1
<b>C</b>	<b>Zinc Coating Requirement (gm/m<sup>2</sup>)</b>	Min 260	Min 270	Min 240	IS 16014:2018 table 8
<b>D</b>	<b>Advance Polymer / PVC Coating Thickness (mm)</b>				
	Requirement of Coating in mm	0.50	0.50	0.50	IS 16014:2018 table 1
	Min.requirement of coating in mm	0.40	0.40	0.40	
<b>E</b>	<b>Adhesion Test</b>	No Flakes After Testing			IS 16014:2018 clause 7.1.2
<b>F</b>	<b>Mesh Opening (Test as per IS 16014)</b>				
	Mesh Size, D (mm)	80			IS 16014:2018 table 9
	Tolerance	(+ 10%) TO (-10%)			
<b>G</b>	<b>Minimum Strength Requirement of Mesh Panel</b>				
(i)	Tensile Strength Parallel to Twist	42.50 kN/m			IS 16014:2018 Clause 6.2 and 11.2 and table 7
(ii)	Tensile Strength Perpendicular to Twist	20.50 kN/m			
(iii)	Selvedge Strength	16.32 kN/m			
(iv)	Punch Strength	21.36 kN/m			
(v)	Panel to Connection Strength (Lacing wire/ Fasteners)	16.32 kN/m			
<b>H</b>	<b>Tolerance in Sack Gabion Box Sizes</b>				
	Length and Diameter	(+ 5%) TO (-5%)			IS 16014:2018 table 1
<b>I</b>	<b>Typical Sack Gabion Sizes</b>				
	Length X Diameter (In meter)	1.50 X 0.74 and 2.0 X 0.96			IS 16014:2018 table 1

**Registered Office:**

Office No 236, Kohinoor Majestic, Plot No. 185 &amp; 186 Chinchwad, Pune, Maharashtra - 411019

**Plant Address:**

GAT No. 318/1, Dongre Wasti Road, At Post Kuruli Taluka Khed, Pune, Maharashtra - 410501

**eMail:**

 reachus@shrisai-india.com  
 reachus@ssgf.in

**Phone:**

 +91 95457 54333  
 +91 98902 97265