

**SSGF make Mechanically woven Double Twisted Hexagonal shape wire mesh Gabion Box Zinc 2.70mm Mesh Wire, 100X120mm Mesh Opening**

Sr.No	Description	Requirements			Compliance
		Mesh	Selvedge	Lacing	
<b>A</b>	<b>Wire Diameter</b>				
	Zinc Coated Wire Diameter (mm)	2.70	3.40	2.20	IS 16014:2018 table 8
	Tolerance level in diameter (mm)	(+/-)0.07	(+/-)0.09	(+/-)0.06	
<b>B</b>	<b>Tensile Strength &amp; Elongation</b>				
	Tensile Strength Requirement N/mm <sup>2</sup>	350 -550 N/mm <sup>2</sup>			IS 16014:2018 clause 6.1
	Elongation Requirement (%)	Minimum 10%			IS 16014:2018 clause 6.1
<b>C</b>	<b>Zinc Coating Requirement (gm/m<sup>2</sup>)</b>	Min 260	Min 270	Min 240	IS 16014:2018 table 8
<b>D</b>	<b>Adhesion Test</b>	No Flakes After Testing			IS 16014:2018 clause 7.1.2
<b>E</b>	<b>Mesh Opening (Test as per IS 16014)</b>				
	Mesh Size, D (mm)	100			IS 16014:2018 table 9
	Tolerance	(+ 10%) TO (-10%)			
<b>F</b>	<b>Minimum Strength Requirement of Mesh Panel</b>				
(i)	Tensile Strength Parallel to Twist	32.00 kN/m			IS 16014:2018 Clause 6.2 and 11.2 and table 7
(ii)	Tensile Strength Perpendicular to Twist	15.50 kN/m			
(iii)	Selvedge Strength	10.20 kN/m			
(iv)	Punch Strength	17.80 kN/m			
(v)	Panel to Connection Strength (Lacing wire/ Fasteners)	10.20 kN/m			
<b>G</b>	<b>Tolerance in Gabion Box Sizes</b>				
	Length and width	(+ 5%) TO (-5%)			IS 16014:2018 table 1
	Height > 0.3 meter	(+ 5%) TO (-5%)			
	Height < 0.3 meter	(+ 10%) TO (-10%)			
<b>H</b>	<b>Typical Gabion Sizes</b>				
	Length X Width X Height (In meter) / <b>Number of Centre Diaphragms</b>	4X1X1 (3nos) , 3X1X1 (2nos) , 2X1X1 (1nos) , 1.5X1X1 (0 nos) , 4X1X0.5 (3nos) , 3X1X0.5 (2nos) , 2X1X0.5 (1nos) , 4X1X0.3 (3nos) , 3X1X0.3 (2nos) , 2X1X0.3 (1nos)			IS 16014:2018 table 1

Office &amp; Plant Address:

GAT No 263, Grampanchayat Milkat No 4413 &amp; 4412, Wadegaon Road, Kesnand, Taluka-Haveli, Pune, India- 412207

eMail:

 reachus@shrisai-india.com  
 reachus@ssgf.in

Phone:

 +91 95457 54333  
 +91 98902 97265